

PREMIUM LINE BATTERIES

for Renewable Energy and Backup Power Applications

PRODUCT LINE SHEET



BATTERY:	Flooded/wet lead-acid battery
DIMENSIONS:	inches (mm)
COLOR:	Maroon (case/cover)
MATERIAL:	Polypropylene

Renewable energy applications operate under challenging conditions such as fluctuating or extreme temperatures, remote locations and the intermittent nature of solar and wind power generation. Designed with a 10-year battery life, Trojan Battery's Premium Line of flooded deep-cycle batteries is specifically engineered to withstand the rigorous conditions of renewable energy applications. The Premium Line incorporates advanced battery features such as Trojan's DuraGrid[™], MaxGuard[®] XL separator and Alpha Plus[®] Paste technologies that provide superior performance, rugged durability and exceptional long life. Trojan's product strategy is focused on one simple objective – manufacture the highest quality battery available in the industry, which is why Trojan's Premium Line is tested to IEC standards.

PRODUCT SPECIFICATION

BCI GROUP SIZE	ТҮРЕ	CAPACITY * Amp-Hours (AH)							ENERGY (kWh)	VOLTACE	TERMINAL	DIMENSIONS ⁸ Inches (mm)			WEIGHT Ibs.
		2-Hr Rate	5-Hr Rate	10-Hr Rate	20-Hr Rate	48-Hr Rate	72-Hr Rate	100-Hr Rate	100-Hr Rate	VOLTAGE	Туре	Length	Width	Height ^c	(kg)
PREMIUM LINE - DEEP-CYCLE FLOODED BATTERIES															
GC2H	T105-RE	146	185	207	225	240	245	250	1.50	6 VOLT	5	10-3/8 (264)	7-1/8 (181)	11-3/4 (299)	67 (30)
903	L16RE-A*	211	267	299	325	346	354	360	2.16	6 VOLT	5	11-5/8 (295)	7 (178)	17-11/16 (450)	115 (52)
903	L16RE-B*	241	303	340	370	394	403	410	2.46	6 VOLT	5	11-5/8 (295)	7 (178)	17-11/16 (450)	118 (54)
903	L16RE-2V*	722	909	1021	1110	1182	1210	1235	2.47	2 VOLT	5	11-5/8 (295)	7 (178)	17-11/16 (450)	119 (54)
The amount of amo-hours (AH) a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 V/cell								* Polvon	"Case						

Capacities are based on peak performance.

B. Dimensions are based on nominal size. Dimensions may vary depending on type of handle or terminal.

C. Dimensions taken from bottom of the battery to the highest point on the battery. Heights may vary depending on type of terminal.

Trojan's battery testing procedures adhere to both BCI and IEC test standards.

CHARGING INSTRUCTIONS

CHARGER VOLTAGE SETTINGS (AT 77°F/25°C)						
	Voltage per cell					
Absorption charge	2.35-2.45					
Float charge	2.20					
Equalize charge	2.58					

Do not install or charge batteries in a sealed or non-ventilated compartment. Constant under or overcharging will damage the battery and shorten its life as with any battery.

OPERATIONAL DATA

OPERATING TEMPERATURE	SELF DISCHARGE	SPECIFIC GRAVITY
-4°F to 113°F (-20°C to +45°C). At temperatures below 32°F (0°C) maintain a state of charge greater than 60%.	4% per month at 80°F (27°C)	The specific gravity at 100% state-of-charge is 1.280

Premium Line batteries manufactured prior to March 2012 have 1.260 SG value.

CHARGING TEMPERATURE COMPENSATION

To the Voltage Reading -- Subtract 0.005 volt per cell (VPC) for every 1°C above 25°C or add 0.005 volt per cell for every 1°C below 25°C.

EXPECTED LIFE VS. TEMPERATURE

Chemical reactions internal to the battery are driven by voltage and temperature. The higher the battery temperature, the faster chemical reactions will occur. While higher temperatures can provide improved discharge performance the increased rate of chemical reactions will result in a corresponding loss of battery life. As a rule of thumb, for every 10°C increase in temperature the reaction rate doubles. Thus, a month of operation at 35°C is equivalent in battery life to two months at 25°C. Heat is an enemy of all lead acid batteries, FLA, AGM and gel alike and even small increases in temperature will have a major influence on battery life.



TERMINAL CONFIGURATIONS 5 LT L-Terminal



Terminal Height Inches (mm) 1-3/4 (43) **Torque Values in-Ib (Nm)** 100 – 120 (11 – 14) **Through-hole Diameter (mm)** 3/8 (10)

VENT CAP





Trojan batteries are available worldwide. We offer outstanding technical support, provided by full-time application engineers. **call 800.423.6569 or + 1.562.236.3000 or visit www.trojanbatteryRE.com** 12380 Clark Street, Santa Fe Springs, CA 90670 • USA or email re@trojanbattery.com

© 2011 Trojan Battery Company. All rights reserved. Trojan Battery Company is not liable for damages that may result from any information provided in or omitted from this publication, under any circumstances. Trojan Battery Company reserves the right to make adjustments to this publication at any time, without notices or obligation.

CAPACITY VS. TEMPERATURE 140 60 50 120 40 100 30 80 Temperature (F) Q 20 Temperature 60 10 40 0 20 -10 0 -20 -20 -30 40 -40 0% 20% 40% 60% 80% 100% 120% Percent of Available Capacity