

12-AGM

inches (mm)

VRLA AGM

Maroon (case/cover)

Polypropylene

MODEL:

BATTERY:

MATERIAL:

COLOR:

DIMENSIONS:

12-AGM	DATA SHEET					
for Renewable Energy and Backup Power Applications						

12	irojan	IX YOUT	11	2
	AGM	157	λ.,	ġ.
		100	1	Ż
		-	1	1

PRODUCT SPECIFICATIONS

BCI GROUP					ENERGY (kWh)	VOLTAGE TERMI	TERMINAL	DIMENSIONS ^B Inches		mm)	WEIGHT Ibs.				
SIZE	ITFE	2-Hr Rate	5-Hr Rate	10-Hr Rate	20-Hr Rate	48-Hr Rate	72-Hr Rate	100-Hr Rate	100-Hr Rate	VOLIAGE	Type ^D	Length	Width	Height ^c	(kg)
	DEEP-CYCLE AGM BATTERIES														
GC12	12-AGM	92	112	127	140	143	143.5	144	1.72	12 VOLT	13	13-9/16 (345)	6-13/16 (174)	10-15/16 (278)	100 (45)

CHARGING INSTRUCTIONS

CHARGER VOLTAGE SETTINGS (AT 77°F/25°C)						
System Voltage	System Voltage 12V		36V	48V		
Absorption Charge	14.1 – 14.7	28.2 – 29.4	42.3 - 44.1	56.4 - 58.8		
Float Charge	13.5	27	40.5	54		

Do not install or charge batteries in a sealed or non-ventilated compartment. Constant under or overcharging will damage the battery and shorten its life as with any battery.

CHARGING TEMPERATURE COMPENSATION

.028 VPC for every 10°F (5.55°C) above or below 77°F (25°C) (add .028 VPC for every 10°F (5.55°C) below 77°F and subtract .028 VPC for every 10°C above 77°F).

EXPECTED LIFE VS. TEMPERATURE

Chemical reactions internal to the battery are driven by voltage and temperature. The higher the battery temperature, the faster chemical reactions will occur. While higher temperatures can provide improved discharge performance the increased rate of chemical reactions will result in a corresponding loss of battery life. As a rule of thumb, for every 10°C increase in temperature the reaction rate doubles. Thus, a month of operation at 35°C is equivalent in battery life to two months at 25°C. Heat is an enemy of all lead acid batteries, FLA, AGM and gel alike and even small increases in temperature will have a major influence on battery life.

OPERATIONAL

Operating Temperature	Self Discharge
-4°F to 113°F (-20°C to +45°C). At temperatures below 32°F (0°C) maintain a state of charge greater than 60%.	Less than 3% per month depending on storage temperature conditions.

A. The amount of amp-hours (AH) a battery can deliver when discharged at a constant rate at 77°F (25°C) and maintain a voltage above 1.75 V/cell. Capacities are based on peak performance.

- B. Dimensions are based on nominal size. Dimensions may vary depending on type of handle or terminal.
- C. Dimensions taken from bottom of the battery to the highest point on the battery. Heights may vary depending on type of terminal
- D. Terminal images are representative only. Trojan's Battery testing procedures adhere to both BCI and IEC test standards. - Additional Terminals Available

TERMINAL CONFIGURATIONS



Made in the USA

PERCENT CAPACITY VS. TEMPERATURE

60 50

40

30

20

10

0

-10

-20


-30

-40

120%

Temperature

BATTERY DIMENSIONS (shown with Inserted Terminal)



140

120

100

⁸⁰

60

40

20

0

-20

-40 +-0%

20%

40%

60%


Percent of Available Capacity

80%


100%

Temperature





TYPICAL CYCLE LIFE IN A STATIONARY APPLICATION





Trojan batteries are available worldwide. We offer outstanding technical support, provided by full-time application engineers. call 800.423.6569 or + 1.562.236.3000 or visit www.trojanbatteryRE.com

12380 Clark Street, Santa Fe Springs, CA 90670 • USA or email re@trojanbattery.com

© 2013 Trojan Battery Company. All rights reserved. Trojan Battery Company is not liable for damages that may result from any information provided in or omitted from this publication, under any circumstances. Trojan Battery Company reserves the right to make adjustments to this publication at any time, without notices or obligation. Please check the Trojan Battery website (www.trojanbattery.com) for the most up-to-date information.

Page 2 of 2