

DEEP-CYCLE AGM BATTERIES

for Renewable Energy and Backup Power Applications

PRODUCT LINE SHEET



BATTERY: VRLA AGM **DIMENSIONS:** Inches (mm)

COLOR: Maroon (case/cover)

MATERIAL: Polypropylene

Trojan's deep-cycle absorbed glass mat (AGM) maintenance-free batteries feature a number of design elements to provide optimum performance. Robust plates extend the life-cycle of Trojan's deep-cycle AGM batteries and a separator of glass fibers serves to isolate the positive and negative plates while acting as a blotter to absorb the electrolyte. The separator is maintained under compression between plates to assure contact with plate surfaces. A computer-generated grid design is optimized for high-power density and the battery's flame arresting, one-way pressure relief vent prevents buildup of excessive pressure. Trojan's deep-cycle AGM batteries are low temperature tolerant, shock and vibration resistant and have a low internal resistance for higher discharge current and higher charging efficiency.

PRODUCT SPECIFICATION

| BCI | TVDF | CAPACITY Amp-Hours (AH) | | | | | | ENERGY (kWh) | VOLTACE | TERMINAL | DIMENSIONS ⁸ Inches (mm) | | | WEIGHT lbs. | |
|---------------|--------------------------|-------------------------|--------------|---------------|---------------|---------------|---------------|-----------------|----------------|----------|-------------------------------------|---------------|---------------|---------------------|----------|
| GROUP SIZE | TYPE | 2-Hr Rate | 5-Hr Rate | 10-Hr Rate | 20-Hr Rate | 48-Hr Rate | 72-Hr Rate | 100-Hr Rate | 100-Hr Rate | VOLTAGE | Туре | Length | Width | Height ^c | (kg) |
| | DEEP-CYCLE AGM BATTERIES | | | | | | | | | | | | | | |
| U1 | U1-AGM | 24 | 29 | 31 | 33 | 33 | 34 | 34 | 0.408 | 12 VOLT | 13 | 8-3/16 (207) | 5-3/16 (132) | 6-13/16 (174) | 27 (12) |
| 22 | 22-AGM | 35 | 43 | 47 | 50 | 51 | 52 | 52 | 0.624 | 12 VOLT | 13 | 9 (229) | 5-1/2 (139) | 8-1/16 (205) | 40 (18) |
| 24 | 24-AGM | 49 | 67 | 70 | 76 | 81 | 83 | 84 | 1.01 | 12 VOLT | 6 | 10-1/4 (260) | 6-5/8 (168) | 9-1/2 (241) | 54 (24) |
| 27 | 27-AGM | 58 | 77 | 82 | 89 | 95 | 97 | 99 | 1.19 | 12 VOLT | 6 | 12-1/16 (306) | 6-13/16 (174) | 8-3/4 (221) | 64 (29) |
| 31 | 31-AGM | 65 | 82 | 92 | 100 | 107 | 109 | 111 | 1.33 | 12 VOLT | 6 | 12-15/16(329) | 6-13/16 (174) | 9-5/16 (237) | 69 (31) |
| GC12 | 12-AGM | 92 | 112 | 127 | 140 | 143 | 143.5 | 144 | 1.72 | 12 VOLT | 13 | 13-9/16 (345) | 6-13/16 (174) | 10-15/16 (278) | 100 (45) |

A. The amount of amp-hours (AH) a battery can deliver when discharged at a constant rate at 77°F (25°C) and maintain a voltage above 1.75 V/cell. Capacities are based on peak performance.

B. Dimensions are based on nominal size. Dimensions may vary depending on type of handle or terminal.

C. Dimensions taken from bottom of the battery to the highest point on the battery. Heights may vary depending on type of terminal. Trojan's battery testing procedures adhere to both BCI and IEC test standards.

CHARGING INSTRUCTIONS

| CHARGER VOLTAGE SETTINGS (AT 77°F/25°C) | | | | | | |
|---|-------------|-------------|-------------|-------------|--|--|
| System Voltage | 12V | 24V | 36V | 48V | | |
| Absorption | 14.1 – 14.7 | 28.2 – 29.4 | 42.3 – 44.1 | 56.4 – 58.8 | | |
| Float | 13.5 | 27 | 40.5 | 54 | | |

Do not install or charge batteries in a sealed or non-ventilated compartment. Constant under or overcharging will damage the battery and shorten its life as with any battery.

OPERATIONAL DATA

| OPERATING TEMPERATURE | SELF DISCHARGE | | | | |
|---|---|--|--|--|--|
| $-4^{\circ}F$ to 113°F (-20°C to $+45^{\circ}C$). At temperatures below 32°F (0°C), maintain a state of charge greater than 60%. | Less than 3% per month depending on storage temperature conditions. | | | | |


CHARGING TEMPERATURE COMPENSATION


.028 VPC for every 10°F (5.55°C) above or below 77°F (25°C) (add .028 VPC for every 10°F (5.55°C) below 77°F and subtract .028 VPC for every 10°C above 77°F).

EXPECTED LIFE VS. TEMPERATURE

Chemical reactions internal to the battery are driven by voltage and temperature. The higher the battery temperature, the faster chemical reactions will occur. While higher temperatures can provide improved discharge performance the increased rate of chemical reactions will result in a corresponding loss of battery life. As a rule of thumb, for every 10°C increase in temperature the reaction rate doubles. Thus, a month of operation at 35°C is equivalent in battery life to two months at 25°C. Heat is an enemy of all lead acid batteries, FLA, AGM and gel alike and even small increases in temperature will have a major influence on battery life.

TYPICAL CYCLE LIFE IN A STATIONARY APPLICATION





TERMINAL CONFIGURATIONS

| 6 | DT | Automotive Post & Stud Terminal | 13 | IT | Insert Terminal |
|---|----|---|----|----|---|
| 1 | | Terminal Height Inches (mm) 29/32 (20) Torque Values in-lb (Nm) AP: 50 – 70 (6 – 8) ST: 120 – 180 (14 – 20) Bolt Size 5/16 – 18 | | | Terminal Height Inches (mm) 4-3/16 (4.7) Torque Values in-lb (Nm) 30 (3 - 4) Bolt Size 10-32UNF |



Trojan batteries are available worldwide.

We offer outstanding technical support, provided by full-time application engineers.

call 800.423.6569 or + 1.562.236.3000 or visit www.trojanbatteryRE.com

12380 Clark Street, Santa Fe Springs, CA 90670 • USA or email re@trojanbattery.com